StandAlone



TISSUE ABSORPTION

For the determination of the water absortion time and water absorbency of tissue.

For







MOST IMPORTANT BENEFITS

- √ Fully-automatic
- ✓ Entire made of stainless steel
- √ Standardized immerse basket (3 g ± 0.1 g)
- ✓ Changeable water container with a capacity of 3 I
- ✓ Digital display of values and statistics



SUBSIDIARY OF Flot Housson

Germany

FRANK-PTI GMBH Auf der Aue 1 69488 Birkenau Tel.: +49 6201 84-0 office@frank-pti.com

Austria

PAPER TESTING INSTRUMENTS GMBH Hauptstrasse 41a (at BDZ) 4663 Laakirchen Tel.: +43 7613 90607-0 office@at.frank-pti.com

www.frank-pti.com



PRODUCT DESCRIPTION

The absorption tester is manufactured from robust stainless steel. The exchangeable water container (3 litre) is lowered and raised via an integrated pneumatic cylinder. The immersion basket is located at an angle of 30° above the raising and lowering mechanism. It swings freely and is attached to the load cell that weights the sample with and without water. The digital display and controls are located on the upper part of the unit at a comfortable height.

TEST DESCRIPTION

A sample weighing approximately 5 grams \pm 0,2 g is placed in the immersion basket. The water container is filled with distilled water and the lifting and lowering mechanism is set. Pushing the start button automatically weighs the sample and the water container is lifted pneumatically. After the sample is completely immersed in the water, the start button is pressed again to determine the immersion time. Once 30 seconds have elapsed the water container is lowered. Excess water then drips back into the container from the sample for 60 seconds. Then the sample is once more weighed and the absorbency of the material is determined. The values, in relation to 1g sample weight, can be read from the digital display as values and statistics.

TECHNICAL DATA

DEVICE/INSTRUMENT

- Standardizied immerse basket (3 g ± 0.1 g)
- Exchangeable water container with a capacity of 3 I
- · Digital display of values and statistics
- Display of absorbed water (g) per 1 g tissue
- Compatible with ProbeNet (see pages 78 81)

INSTALLATION REQUIREMENTS

Electrical connection	100 – 230 V / 50 – 60 Hz
Water connection	No
Compressed air	4 - 6 bar

APPLICABLE STANDARDS

• DIN EN ISO 12625-8



Immerse basket and exchangeable water container